

TEX-NEO60

60 Duro Neoprene Sheet 36" & 48" Wide



General Properties and Applications

The most widely used sheet for general applications, including gaskets, sealing, cushioning and weather-stripping. Provides medium oil and ozone resistance. Our exclusive post-cure process provides a smooth and clean finish that is free of talc, a must for PSA applications.

TECHNICAL DATA

| | |
|------------------|---------------------|
| Durometer | 60 +/-5 |
| Color | Black |
| Temperature | -20°F to +190°F |
| Tensile Strength | 1,000 psi |
| Elongation | 350% |
| Specifications | ASTM D2000-M1-BC607 |



| Width | Gauge | Part Number | Ln. Ft./Roll | Sq. Yds./Roll | Lbs./Roll |
|-------|-------|-------------|--------------|---------------|-----------|
| 36" | 1/32" | NEO-1-36 | 150' | 50 | 104 |
| | 3/64" | NEO-364-36 | 100' | 33.3 | 104 |
| | 1/16" | NEO-2-36 | 100' | 33.3 | 139 |
| | 3/32" | NEO-3-36 | 75' | 25 | 156 |
| | 1/8" | NEO-4-36 | 50' | 16.7 | 139 |
| | 3/16" | NEO-6-36 | 50' | 16.7 | 208 |
| | 1/4" | NEO-8-36 | 50' | 16.7 | 278 |
| | 3/8" | NEO-12-36 | 25' | 8.33 | 208 |
| | 1/2" | NEO-16-36 | 25' | 8.33 | 278 |
| | 5/8" | NEO-20-36 | 25' | 8.33 | 347 |
| | 3/4" | NEO-24-36 | 25' | 8.33 | 418 |
| | 1" | NEO-32-36 | 25' | 8.33 | 557 |
| 48" | 1/32" | NEO-1-48 | 150' | 66.7 | 139 |
| | 1/16" | NEO-2-48 | 100' | 44.4 | 185 |
| | 3/32" | NEO-3-48 | 75' | 19.8 | 208 |
| | 1/8" | NEO-4-48 | 50' | 22.2 | 185 |
| | 3/16" | NEO-6-48 | 50' | 22.2 | 278 |
| | 1/4" | NEO-8-48 | 50' | 22.2 | 370 |
| | 3/8" | NEO-12-48 | 25' | 11.1 | 278 |
| | 1/2" | NEO-16-48 | 25' | 11.1 | 357 |
| | 5/8" | NEO-20-48 | 25' | 11.1 | 463 |
| | 3/4" | NEO-24-48 | 25' | 11.1 | 557 |
| | 1" | NEO-32-48 | 25' | 11.1 | 742 |