

Tex-FKM

FLUOROCARBON SHEET

General Properties and Applications

Premium Grade Fluorelastomer sheet, Type A (66%+ Fluorine) for the most demanding applications.

Technical Data

Durometer	75+/-5
Color	Black, Smooth, Cinnamon Scented
Tensile Strength	1000 psi
Elongation	225%
Temperature Range	-20°F to +350°F
MIL Spec	R-83248 Type II Class I

Width (in.)	Gauge (in.)	Part Number	Ln Ft/ Roll	Sq Yds/ Roll	Lbs/ Roll
48"	1/16"	FKM-2	51'	22.67	124
	1/8"	FKM-4	51'	22.67	247
	3/16"	FKM-6	51'	22.67	371
	1/4"	FKM-8	51'	22.67	494
	3/8"	FKM-12	27'	12	371
	1/2"	FKM-16	27'	12	494

① Certificates of Conformance indicating production date and lot code are available on request at the time of order.

① Sold by the LINEAR YARD only, one (1) linear yard minimum.

