

Tex-NEO 50

50 DURO COMMERCIAL NEOPRENE SHEET



General Properties and Applications

A softer durometer neoprene used for gaskets and sealing where surface irregularities or configuration requires a more pliable material. Our exclusive post-cure process provides a smooth and clean finish free of talc, a must for PSA applications.

Technical Data

Durometer	50 +/-5
Color	Black
Tensile Strength	1,100 psi
Elongation	350%
Temperature Range	-20°F to +190°F
Continuous Lay Line	Includes style, durometer, and lot code
ASTM Line Call Out	D2000-M2-BC507-A14-B14-F17

Width (in.)	Gauge (in.)	Part Number	Ln Ft/ Roll	Sq Yds/ Roll	Lbs/ Roll
48"	1/16"	NEO50-2	54'	24	100
	1/8"	NEO50-4	27'	12	100
	3/16"	NEO50-6	36'	16	200
	1/4"	NEO50-8	27'	12	200

- ① Talc-free surface eliminates the need to clean the sheet rubber and is ideal for PSA applications.
- ① Certificates of Conformance indicating production date and lot code are available on request at the time of order.



Tex-TIP:

Visit us online today at www.texcelrubber.com for useful features such as a Measurement Conversion Tool and a comprehensive Chemical Resistance Chart.

