

# Tex-NEO 60

## 60 DURO COMMERCIAL NEOPRENE SHEET



### General Properties and Applications

The most widely used sheet for general applications including gaskets, sealing, cushioning, and weather stripping. Provides medium oil and ozone resistance. Our exclusive post-cure process provides a smooth and clean finish free of talc, a must for PSA applications.

### Technical Data

Durometer	60 +/-5
Color	Black
Tensile Strength	1,100 psi
Elongation	350%
Temperature Range	-20°F to +190°F
Continuous Lay Line	Includes style, durometer, and lot code
ASTM Line Call Out	D2000-M2-BC607-A14-B14-F17

Width (in.)	Gauge (in.)	Part Number	Ln Ft/ Roll	Sq Yds/ Roll	Lbs/ Roll
36"	1/32"	NEO-1-36	144'	48	100
	3/64"	NEO-364-36	96'	32	100
	1/16"	NEO-2-36	72'	24	100
	3/32"	NEO-3-36	48'	16	100
	1/8"	NEO-4-36	36'	12	100
	3/16"	NEO-6-36	48'	16	200
	1/4"	NEO-8-36	36'	12	200
	3/8"	NEO-12-36	24'	8	200
	1/2"	NEO-16-36	18'	6	200
	3/4"	NEO-24-36	21'	7	351
	1"	NEO-32-36	21'	7	468
48"	1/16"	NEO-2-48	54'	24	100
		NEO-2-48-100	100'	44.4	185
	1/8"	NEO-4-48	27'	12	100
		NEO-4-48-50	50'	22.2	185
	3/16"	NEO-6-48	36'	16	200
	1/4"	NEO-8-48	27'	12	200
	3/8"	NEO-12-48	18'	8	200
	1/2"	NEO-16-48	14'	6.2	200
	3/4"	NEO-24-48	21'	9.3	468
	1"	NEO-32-48	21'	9.3	624

