

Tex-RED

RED SBR SHEET



General Properties and Applications

The industry's general service rubber for common gasketing applications, such as water. Not recommended for applications with oil. Our exclusive post-cure process provides a smooth and clean finish free of talc, a must for PSA applications.

Technical Data

| | |
|--------------------|--|
| Durometer | 73 +/-5 |
| Color | Red |
| Tensile Strength | 700 psi |
| Elongation | 300% |
| Temperature Range | -20°F to +180°F |
| ASTM Line Call Out | <ul style="list-style-type: none"> ▪ D2000-M2-AA703-A13-B13-EA14 ▪ Meets D1330 Grade I |

| Width (in.) | Gauge (in.) | Part Number | Ln Ft/ Roll | Lbs/ Roll |
|----------------|----------------|----------------|----------------|--------------|
| 36" | 1/16" | RED-2-36 | 60' | 100 |
| | 1/8" | RED-4-36 | 30' | 100 |
| | 3/16" | RED-6-36 | 40' | 200 |
| | 1/4" | RED-8-36 | 30' | 200 |
| 48" | 1/16" | RED-2-48 | 45' | 100 |
| | | RED-2-48-100 | 100' | 220 |
| | 1/8" | RED-4-48 | 22.5' | 100 |
| | | RED-4-48-50 | 50' | 215 |
| | 3/16" | RED-6-48 | 30' | 200 |
| | 1/4" | RED-8-48 | 22.5' | 200 |

- ① Talc-free surface eliminates the need to clean the sheet rubber and is ideal for PSA applications.
- ① Certificates of Conformance indicating production date and lot code are available on request at the time of order.

