

Tex-NEO 40

40 DURO COMMERCIAL NEOPRENE SHEET



General Properties and Applications

A softer durometer neoprene used for gaskets and sealing where surface irregularities or configuration requires a more pliable material. Our exclusive post-cure process provides a smooth and clean finish free of talc, a must for PSA applications.

Technical Data

Durometer	40 +/-5
Color	Black
Tensile Strength	1,100 psi
Elongation	450%
Temperature Range	-20°F to +190°F
Continuous Lay Line	Includes style, durometer, and lot code
ASTM Line Call Out	D2000-M2-BC407-A14-B14-F17

Width (in.)	Gauge (in.)	Part Number	Ln Ft/ Roll	Sq Yds/ Roll	Lbs/ Roll
48"	1/16"	NEO40-2-48	50'	22.2	94
	1/8"	NEO40-4-48	50'	22.2	188
	3/16"	NEO40-6-48	50'	22.2	282
	1/4"	NEO40-8-48	50'	22.2	377

- ① Talc-free surface eliminates the need to clean the sheet rubber and is ideal for PSA applications.
- ① Certificates of Conformance indicating production date and lot code are available on request at the time of order.



Tex-TIP:

Texcel does not impose a minimum on the number of rolls per order. This makes purchasing easy if you need to purchase just one roll of a type or size that does not move often.

