

TEX-PC-EPDM

Peroxide-Cured EPDM Sheet



General Properties and Applications

EPDM sheet for ozone and sunlight resistance. Peroxide-cured compound to achieve even higher temperature ratings and improved ozone resistance over traditional sulfur-cured EPDM sheet.







Note:

- Not recommended for applications in which oil resistance is necessary.

TECHNICAL DATA

Durometer	60 +/-5
Color	Black
Temperature	-49°F to +300°F intermittent
Tensile Strength	1,800 psi
Elongation	350%
Specifications	ASTM D2000-M1-BA612



 Width	 Gauge	 Part Number	 Ln. Ft./Roll	 Sq. Yds./Roll	 Lbs./Roll
48"	1/16"	EPDM-PC-2-48	50'	22.2	78
	1/8"	EPDM-PC-4-48	50'	22.2	156
	3/16"	EPDM-PC-6-48	50'	22.2	234
	1/4"	EPDM-PC-8-48	50'	22.2	312