CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
0-AMINOTOLUENE	I	I	I	I	I	I	I
1,4-DIOXANE	A	X	X	I	X	I	A
1-AMINO-2-PROPANOL	I	I	I	I	I	I	I
1-AMINOBUTANE	I	I	I	I	I	I	I
1-AMINOPENTANE	I	I	I	I	I	I	I
1-BROMO-2 METHYL PROPANE	I	I	I	I	I	I	I
1-BROMO-3 METHYL BUTANE	I	I	I	I	I	I	I
1-BROMOBUTANE	I	I	I	I	I	I	I
1-CHLORO-2-METHYL PROPANE	I	I	I	I	I	I	I
1-CHLORO-3-METHYL BUTANE	I	I	I	I	I	I	I
1-DECANOL	I	A	I	I	A	I	A
1-HENDACONAL	I	I	I	I	I	I	I
1-UNDECANOL	I	A	I	I	A	I	A
2 (2AMINOETHYLAMINO) ETHANOL	I	I	I	I	I	I	I
2 (2ETHOXYETHOXY) ETHANOL	I	I	I	I	I	I	I
2 (2ETHOXYETHOXY) ETHYL ACETATE	I	I	I	I	I	I	I
2,4-DI-SEC-PENTYLPHENOL	I	I	I	I	I	I	I
2-AMINOETHANOL	I	A	I	I	A	I	I
2-CHLORO-1-HYDROXY-BENZENE	I	I	I	I	I	I	I
2-CHLOROPHENOL	X	X	X	X	X	I	A
2-CHLOROPROPANE	X	X	X	I	X	I	A
2-ETHOXYETHANOL	I	I	I	I	I	I	I
2-ETHOXYETHYL ACETATE	I	I	I	I	I	I	I
2-ETHYL (BUTYRALDEHYDE)	I	X	I	I	X	I	A
2-ETHYL-1-HEXANOL	A	A	A	A	A	I	A
2-ETHYLHEXANOIC ACID	I	I	I	I	I	I	I
2-ETHYLHEXYL ACETATE	I	I	I	I	I	I	I
2-OCTANONE	I	I	I	I	I	I	I
3-BROMOPROPENE	I	I	I	I	I	I	I
3-CHLORO-2-METHYL PROPANE	I	I	I	I	I	I	I
3-CHLOROPROPENE	I	I	I	I	I	I	I
3OAL OIL	I	I	I	I	I	I	A
4-HYDROXY-4-METHYL-2-PENTANONE	I	I	I	I	I	I	I
ACETALDEHYDE	A	I	F	X	X	A	A
ACETIC ACID, 10%	A	F	F	X	F	A	A
ACETIC ACID, 50%	A	A	X	X	X	A	A
ACETIC ACID, GLACIAL	A	X	X	C	X	A	A
ACETIC ANHYDRIDE	A	F	A	X	X	A	A
ACETIC OXIDE	I	F	I	I	A	I	A
ACETONE	A	C	X	X	C	A	A
ACETONE CYANOHYDRIN	I	F	I	I	F	A	A
ACETONITRILE	I	I	I	I	I	I	I
ACETOPHENONE	A	X	X	X	X	X	X
ACETYL ACETONE	A	X	X	X	X	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
ACETYL CHLORIDE	X	X	X	X	X	A	A
ACETYL OXIDE	I	F	I	I	A	A	A
ACETYLENE	A	A	A	A	A	A	A
ACETYLENE DI+ TETRA CHLORIDE	I	X	I	I	X	I	A
ACROLEIN	I	A	I	I	F	I	A
ACRYLENITRILE	X	X	X	X	X	I	C
ACRYLIC ACID	I	I	I	I	I	I	I
ADIPIC ACID	A	I	A	A	A	I	I
AIR, +300F	X	X	X	X	X	X	I
ALK-TRI	I	X	I	X	I	I	A
ALLYL ALCOHOL	I	A	I	I	A	A	A
ALLYL BROMIDE	I	X	I	I	X	A	A
ALLYL CHLORIDE	I	X	I	I	X	A	A
ALUM	A	A	A	A	A	A	A
ALUMINUM ACETATE (AQ)	A	X	A	F	X	A	A
ALUMINUM CHLORIDE (AQ)- 40%	A	A	A	A	A	A	A
ALUMINUM FLUORIDE	A	A	A	A	A	A	A
ALUMINUM FORMATE	I	X	I	I	X	A	A
ALUMINUM HYDROXIDE	I	A	A	A	I	A	I
ALUMINUM NITRATE (AQ)	A	A	A	A	A	A	A
ALUMINUM SULFATE (AQ)	A	A	A	A	A	A	A
ALUMS-NH3-CR-K	A	A	A	A	A	I	I
AMINES-MIXED	A	A	A	X	A	I	I
AMINOBENZENE	I	I	I	I	I	I	I
AMINODIMETHYLBENZENE	I	I	I	I	I	I	I
AMINOETHANE	I	I	I	I	I	I	I
AMINOXYLENE	I	I	I	I	I	I	I
AMMONIUM CARBONATE (AQ)	A	A	A	X	A	I	I
AMMONIUM CHLORIDE (AQ)	A	A	A	A	A	A	A
AMMONIUM HYDROXIDE	A	X	A	X	X	A	A
AMMONIUM NITRATE(AQ)	A	I	A	A	A	A	A
AMMONIUM PHOSPHATE, DIBASIC	A	A	A	A	A	A	A
AMMONIUM SULPHATE (AQ)	A	A	A	A	A	A	A
AMMONIUM SULPHITE	I	A	I	I	A	I	A
AMMONIUM THIOSULPHATE	I	A	I	I	A	I	A
AMYL ACETATE	X	X	X	X	X	A	A
AMYL ACETONE	I	X	I	I	X	I	A
AMYL ALCOHOL	A	A	A	X	A	A	A
AMYL BROMIDE	I	I	I	I	I	I	I
AMYL CHLORIDE	X	X	X	I	X	A	A
AMYL ETHER	I	I	I	I	I	I	I
AMYLAMINE	I	A	I	I	A	I	I
ANETHOLE	I	X	I	I	X	A	A
ANILINE	C	X	X	X	X	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
ANILINE DYES	A	A	A	X	A	A	A
ANILINE OIL	A	X	X	X	X	I	I
ANIMAL FATS	C	X	C	A	X	A	A
ANTIMONY PENTACHLORIDE	I	X	I	I	X	I	A
AQUA REGIA	C	X	X	X	X	X	X
ARGON	A	X	X	C	X	A	A
ARSENIC ACID	A	A	A	A	A	I	A
ASPHALT	X	X	X	X	X	X	X
ASTM FUEL A	X	X	A	A	X	A	A
ASTM FUEL B	X	X	X	A	X	A	A
ASTM FUEL C	X	X	X	A	X	A	A
ASTM OIL NO. 1	X	X	A	A	X	A	A
ASTM OIL NO. 2	X	X	A	A	X	A	A
ASTM OIL NO. 3	X	X	X	A	X	A	A
ASTM OIL NO. 4	X	X	X	A	X	A	A
AUTOMATIC TRANSMISSION FLUID	X	X	A	A	X	A	A
BANANA OIL	C	I	I	X	X	A	A
BARIUM CHLORIDE (AQ)	A	A	A	A	A	A	A
BARIUM HYDROXIDE (AQ)	A	A	A	A	A	A	A
BARIUM SULFIDE (AQ)	A	A	A	A	A	A	A
BEER	A	A	A	C	A	A	A
BEET SUGAR LIQUORS	A	A	A	A	A	A	A
BENZAL CHLORIDE	I	I	I	I	I	A	A
BENZALDEHYDE	A	X	X	X	X	I	A
BENZENE	X	X	X	X	X	A	A
BENZENE CARBOXYLIC ACID	I	I	I	I	I	I	I
BENZINE	X	X	A	A	X	I	A
BENZOIC ACID	X	X	X	X	X	I	A
BENZOL	X	I	I	X	I	A	I
BENZOTRICHLORIDE	I	I	I	I	I	A	A
BENZYL ACETATE	I	X	I	I	X	A	A
BENZYL ALCOHOL	X	X	C	X	X	A	A
BENZYL CHLORIDE	A	C	X	X	C	A	A
BENZYL ETHER	I	I	I	I	I	I	I
BIS (2-CLOROETHYL) ETHER	I	I	I	I	I	I	I
BLACK SULFATE LIQUOR	A	A	A	A	A	A	I
CADMIUM ACETATE	I	X	I	I	X	A	A
CALCIUM ACETATE	A	X	A	A	X	A	A
CALCIUM ALUMINATE	I	A	I	I	A	I	A
CALCIUM BICHROMATE	I	I	I	I	I	I	A
CALCIUM BISULFIDE	X	I	C	A	I	I	I
CALCIUM CHLORIDE	A	A	A	A	A	A	A
CALCIUM HYDROXIDE	A	A	A	A	A	A	A
CALCIUM HYPOCHLORITE	A	X	X	X	X	C	C

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
CALCIUM NITRATE	A	A	A	A	A	A	A
CALCIUM SULFIDE	A	A	A	A	A	A	A
CARBAMIDE	I	I	I	I	I	I	I
CARBITOL	A	X	A	A	X	A	A
CAPRYLIC ACID	I	F	I	I	X	A	A
CARBOLIC ACID PHENOL	A	X	X	X	X	A	A
CARBON DIOXIDE	C	A	C	X	A	A	A
CARBON DISULFIDE	X	X	X	X	X	A	C
CARBON MONOXIDE	C	A	C	A	A	A	A
CARBON TETRACHLORIDE	X	X	X	X	X	A	A
CARBONIC ACID	A	A	X	X	A	I	A
CASTOR OIL	A	F	A	A	A	A	A
CAUSTIC SODA (SODIUM HYDROXIDE)	I	I	I	I	I	I	I
CELLOSOLVE ACETATE	A	X	X	X	X	A	A
CELLUGUARD	A	A	A	A	A	I	I
CETYLIC ACID	I	I	I	I	I	I	I
CHINA WOOD OIL (TUNG OIL)	X	X	A	A	X	I	I
CHLORINATED SOLVENTS	X	X	X	X	X	I	A
CHLORO-2-PROPANONE	I	I	I	I	I	I	I
CHLOROACETIC ACID	X	X	X	X	X	A	A
CHLOROACETONE	A	X	X	X	X	A	A
CHLOROBENZENE	X	X	X	X	X	A	A
CHLOROBUTANE	I	X	I	I	X	A	A
CHLORODANE	A	I	I	A	I	I	I
CHLOROETHYL BENZENE	I	X	I	I	X	A	A
CHLOROFORM	X	X	X	X	X	A	A
CHLOROPENTANE	I	X	I	I	X	A	A
CHLOROSULFONIC ACID	X	X	C	X	X	X	A
CHLOROTOLUENE	X	X	X	X	X	A	A
CHLOROX	A	X	A	A	X	A	I
CHROME PLATING SOLUTIONS	A	X	X	X	X	A	I
CHROMIC ACID	C	X	X	X	X	I	A
CHROMIUM TRIOXIDE	I	I	I	I	I	I	I
CINNAMENE	I	I	I	I	I	I	I
CIS-9-OCTADECENOIC ACID	I	X	I	I	X	I	A
CITRIC ACID	A	A	A	A	A	A	A
COAL OIL	X	X	I	X	X	A	A
COAL TAR	X	X	A	A	X	A	A
COAL TAR NAPTHA	I	X	I	I	X	I	A
COCONUT OIL	C	X	A	A	X	A	A
COKE OVEN GAS	X	X	X	X	X	I	A
COOLANOL (MONSANTO)	X	X	A	A	X	I	I
COPPER CHLORIDE	A	F	C	C	A	A	A
COPPER CYNAIDE	A	A	A	A	A	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
COPPER HYDRATE	I	F	I	I	A	A	A
COPPER HYDROXIDE	I	F	I	I	A	I	A
COPPER SULFATE	A	F	A	A	A	A	A
CORN OIL	C	X	C	A	X	A	A
COTTONSEED OIL	C	X	C	C	X	A	C
CREOSOTE	X	X	C	C	X	A	A
CRESOLS	X	X	X	X	X	A	A
CRESYLIC ACID	X	X	X	X	X	A	A
CROTONALDEHYDE	I	X	I	I	X	A	A
CRUDE OIL	X	X	X	A	X	A	A
CUMENE	X	X	X	X	X	A	A
CUPRIC CARBONATE	I	F	I	I	A	A	A
CUPRIC HYDROXIDE	I	I	I	I	I	I	I
CUPRIC NITRATE	I	F	I	I	A	A	A
CUPRIC SULFATE	I	F	I	I	A	A	A
CUTTING OIL	X	X	A	A	X	I	I
CYCLOHEXANE	X	X	X	A	X	A	A
CYCLOHEXANOL	X	X	A	C	X	A	A
CYCLOHEXANONE	X	X	X	X	X	A	A
CYCLOPENTANE	I	X	I	I	X	A	A
CYCLOPENTANOL	I	X	I	I	X	A	A
CYCLOPENTANONE	I	X	I	I	X	I	A
CYCLOPENTYL ALCOHOL	I	I	I	I	I	I	I
D-FURALDEHYDE	I	I	I	I	I	I	I
DDT IN KEROSENE	X	X	F	A	X	I	A
DECAHYDRONAPTHALENE	I	I	I	I	I	I	I
DECAHYDROXYNAPTHALENE	I	I	I	I	I	I	I
DECALIN	I	X	I	I	X	X	A
DECYL ALCOHOL	I	A	I	I	A	A	A
DECYL ALDEHYDE	I	X	I	I	X	A	A
DECYL BUTYL PTHALATE	I	X	I	I	X	A	A
DECYL CARBINOL	I	I	I	I	I	I	I
DETERGENT, WATER SOLUTION	A	A	A	A	A	I	I
DEVELOPING FLUID (PHOTO)	A	A	A	A	A	I	I
DEXTRON	X	X	A	A	X	I	I
DI(2ETHYLHEXYL) ADIPATE	I	I	I	I	I	I	I
DI(2ETHYLHEXYL) PTHALATE	I	I	I	I	I	I	I
DI-ISO-BUTYLENE	X	X	X	A	X	I	A
DI-ISO-DECYPTHALATE	I	I	I	I	I	I	I
DI-ISO-PROPANOLAMINE	I	I	I	I	I	I	I
DI-ISO-PROPYL ETHER	I	X	I	I	X	I	A
DI-ISO-PROPYL KETONE	A	X	X	X	X	I	A
DI-P-MENTHA-1,8-DIENE	I	I	I	I	I	I	I
DIACETONE ALCOHOL	X	X	X	X	X	A	C

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
DIACETYLMETHANE	I	I	I	I	I	I	I
DIALLYPTHALATE	I	I	I	I	I	I	I
DIAMMONIUM PHOSPHATE	I	I	I	I	I	I	I
DIAMYL NAPTHALENE	I	X	I	I	X	I	A
DIAMYLAMINE	I	F	I	I	A	I	I
DIAMYLENE	I	X	I	I	X	I	A
DIAMYLPHENOL	I	X	I	I	X	I	A
DIBENZYL ETHER	X	X	X	X	X	A	A
DIBROMOBENZENE	I	X	I	I	X	A	A
DIBROMOMETHANE	I	I	I	I	I	I	I
DIBUTYL ETHER	C	X	X	X	X	A	A
DIBUTYL PTHALATE	C	X	X	X	X	A	A
DIBUTYL SEBACATE	A	X	X	X	X	A	A
DIBUTYLAMINE	X	X	X	X	X	I	A
DICALCIUM PHOSPHATE	I	A	I	I	A	I	A
DICHLORO ETHYLENE	I	I	I	I	I	I	I
DICHLOROACETIC ACID	I	A	I	I	X	I	A
DICHLOROBENZENE	X	X	X	X	X	A	A
DICHLOROBENZENE	C	C	C	A	X	A	A
DICHLORODIFLUOROMETHANE	I	X	I	I	X	I	I
DICHLOROETHANE	I	X	I	I	X	I	A
DICHLOROETHYL ETHER	I	X	I	I	X	I	A
DICHLOROHEXANE	I	X	I	I	X	A	A
DICHLOROMETHANE	I	X	I	I	X	A	A
DICHLOROPENTANE	I	X	I	I	X	A	A
DICHLOROPROPANE	I	X	I	I	X	A	A
DICHLOROPROPENE	I	I	I	I	I	A	A
DICHLOROTOLUENE	I	I	I	I	I	I	I
DIESEL OIL	X	X	C	A	X	A	C
DIETHANOL AMINE	I	A	I	I	A	A	I
DIETHYL ETHER	X	X	C	X	X	I	A
DIETHYL KETONE	I	F	I	I	X	I	A
DIISOBUTYL KETONE	A	X	X	X	X	I	A
DIETHYL OXALATE	I	A	I	I	A	I	A
DIETHYL PTHALATE	A	X	X	I	X	A	A
DIETHYL SEBACATE	C	X	X	X	X	I	I
DIETHYL SULFATE	I	I	I	I	I	I	I
DIETHYLAMINE	A	A	C	C	A	A	C
DIETHYLBENZINE	X	X	X	X	X	A	A
DIETHYLENE GLYCOL	A	A	A	A	A	A	C
DIETHYLENE OXIDE	I	I	I	I	I	I	I
DIETHYLENETRIAMINE	I	A	I	I	A	A	I
DIETHYLTRIAMINE	I	A	I	I	A	A	I
DIHYDROXY DIETHYL ETHER	I	I	I	I	I	I	I

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
DIHYDROXY SUCCINIC ACID	I	I	I	I	I	I	A
DIISOBUTYL KETONE	A	X	X	X	X	A	A
DIISODECTYL PTHALATE	I	X	I	I	X	A	A
DIISOOCTYL ADIPATE	I	X	I	I	X	A	A
DIISOOCTYL PTHALATE	I	X	I	I	X	A	A
DIMETHALAMINE	I	I	I	I	I	A	A
DIMETHYL CARBINOL	I	I	I	I	I	A	I
DIMETHYL KETONE	I	I	I	I	I	A	I
DIMETHYL LANILINE	A	I	C	C	C	A	I
DIMETHYL PTHALATE	A	X	X	X	X	A	A
DIMETHYL SULFATE	I	I	I	I	I	I	I
DIMETHYL SULFIDE	I	I	I	I	I	I	I
DIMETHYL-3-PENTANONE	I	I	I	I	I	I	I
DIMETHYL-4-HEPTANONE	I	I	I	I	I	I	I
DIMETHYLBENZENE	I	I	I	I	I	A	I
DIMETHYLBUTANE	I	I	I	I	I	I	I
DIOCTYL ADIPATE	I	I	I	I	I	A	I
DIOCTYL PTHALATE	C	X	X	C	X	A	A
DIOXALANE	A	X	X	X	X	A	A
DIOXANE	A	X	X	X	X	A	I
DIPENTENE	X	X	X	A	X	I	I
DIPENTYLAMINE	I	I	I	I	I	I	I
DIPROPYLAMINEOLAMINE	I	A	I	I	A	I	I
DIPROPYLENE GLYCOL	I	A	I	I	A	I	I
DISODIUM PHOSPHATE	I	A	I	I	A	A	A
DIVINYL BENZENE	I	X	I	I	X	A	A
DOWELL INHIBITOR	I	I	I	I	I	I	I
DOWFAX 2A1 SOLVENT	I	I	I	I	I	I	I
DOWFAX 2A1 TA	I	I	I	I	I	I	I
DOWFAX 6A1 TZ	I	I	I	I	I	I	I
DOWTHERM, A AND E	X	X	X	X	X	A	A
DOWVAX 6A1 SOLVENT	I	I	I	I	I	I	I
DRY CLEANING FLUIDS	X	I	X	C	X	I	I
DURO AW16, 31	X	I	I	A	I	I	I
DURO FR-HD	X	I	I	A	I	I	I
ETHANOIC ACID	I	I	I	I	I	I	I
ETHANOL (GRAIN ALCOHOL)	A	A	A	C	A	A	A
ETHANOLAMINE	A	A	A	A	A	A	A
ETHERS	C	X	X	X	X	I	I
ETHYL ACETATE	C	X	X	X	X	A	A
ETHYL ACETOACETATE	A	X	X	X	X	A	A
ETHYL ALCOHOL	A	A	A	C	A	A	A
ETHYL ALDEHYDE	I	F	I	I	I	A	A
ETHYL ALUMINUM DICHLORIDE	A	X	X	X	X	C	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
ETHYL BENZENE	X	X	X	X	X	A	A
ETHYL BROMIDE	X	X	X	A	I	I	I
ETHYL CELLULOSE	A	A	A	A	A	C	A
ETHYL CHLORIDE	X	X	X	X	X	C	A
ETHYL DICHLORIDE	I	X	I	I	X	C	A
ETHYL DIISOBUTYLTHIO-CARBAMATE	I	A	I	I	A	C	A
ETHYL ETHER	X	X	X	C	X	A	A
ETHYL FORMATE	A	X	A	X	X	A	A
ETHYL IODIDE	I	X	I	I	X	A	A
ETHYL OXALATE	X	X	X	X	X	A	A
ETHYL PTHALATE	I	I	I	I	I	A	I
ETHYL SILICATE	A	F	A	A	F	A	A
ETHYL-1-BUTANOL	I	A	I	I	A	I	A
ETHYL-N-BUTYL KETONE	I	X	I	I	X	I	A
ETHYLACETONE	I	I	I	I	I	I	I
ETHYLACRYLATE	A	X	X	X	X	A	A
ETHYLALCOHOL	A	A	A	C	A	A	A
ETHYLAMINE	I	F	I	I	F	A	I
ETHYLBUTYLACETATE	I	X	I	I	X	A	A
ETHYLBUTYLALCOHOL	I	A	I	I	A	A	A
ETHYLENE CHLOROHYDRIN	C	A	C	X	A	A	A
ETHYLENE DIAMINE	A	A	A	A	A	A	A
ETHYLENE DIBROMIDE	C	X	X	X	X	A	A
ETHYLENE DICHLORIDE	X	X	X	X	X	A	A
ETHYLENE G.MONOBUTYL ETHER	I	I	I	I	I	I	A
ETHYLENE G.MONOETHYL E ACETATE	I	I	I	I	A	I	I
ETHYLENE G.MONOETHYL ETHER	I	I	I	I	I	I	A
ETHYLENE G.MONOHEXYL ETHER	C	X	X	X	X	C	A
ETHYLENE GLYCOL	A	A	A	A	A	A	C
ETHYLENE OXIDE	C	X	X	X	X	I	I
FATTY ACIDS	X	X	C	C	X	A	A
FAURAN	C	X	X	X	X	I	I
FERRIC BROMADE	I	A	I	I	A	A	A
FERRIC CHLORIDE	A	A	A	A	A	A	A
FERRIC NITRATE	A	A	A	A	A	A	A
FERRIC SULFATE	A	A	A	A	A	A	A
FERROUS ACETATE	I	X	I	I	X	I	A
FERROUS CHLORIDE	A	A	A	A	A	A	A
FERROUS SULFATE	A	A	A	A	A	A	A
FLUOBORIC ACID	A	A	C	C	A	C	C
FLUORINE	X	X	X	X	X	A	A
FLUOSILICIC ACID	A	A	C	C	C	C	C
FORMALDEHYDE	A	A	C	C	C	C	C
FORMALIN	I	A	I	I	A	I	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
FORMIC ACID	A	A	C	X	A	A	C
FREON 113	C	C	A	A	A	I	I
FREON 12	X	X	A	A	X	I	C
FREON 22	I	X	X	X	X	I	C
FREON SO2	A	I	A	I	I	I	I
FUEL A (ASTM)	X	X	A	A	X	I	A
FUEL B (ASTM)	X	X	F	A	X	I	A
FUEL OIL	X	X	A	A	X	A	C
FURFURAL	C	X	X	X	X	A	A
FURFURAN	C	X	X	X	X	I	I
FURFURYL ALCOHOL	X	X	A	A	X	A	A
GALLIC ACID	A	A	X	C	C	A	C
GALLOTANNIC ACID	I	I	I	I	I	I	I
GAS, COAL	I	I	I	I	I	I	I
GAS, HIGH OCTANE	X	I	X	A	I	C	I
GASOLINE	X	X	X	A	X	A	A
GLACIAL ACRYLIC ACID	I	I	I	I	I	I	A
GLUCONIC ACID	I	X	I	I	X	A	A
GLUCOSE	A	A	A	A	A	A	A
GLYCERINE	A	A	A	A	A	I	C
GLYCEROL	A	A	A	A	A	I	I
GLYCOGENIC ACID	I	I	I	I	I	I	I
GLYCONIC ACID	I	I	I	I	I	I	I
GLYCYL ALCHOHOL	I	I	I	I	I	I	I
GREASE	X	X	X	A	X	A	A
GREEN SULFATE LIQUOR	A	A	A	A	A	A	A
GYLCOLS	A	A	A	A	A	A	A
HALON 1211	I	I	A	A	I	I	I
HELIUM	A	A	A	A	A	I	I
HEPTALDEHYDE	I	I	I	I	I	I	I
HEPTANAL	I	X	I	I	X	A	A
HEPTANE	X	X	A	A	X	A	A
HEPTANE CARBOXYLIC ACID	I	I	I	I	I	I	I
HEPTANOIC ACID	I	I	I	I	I	I	I
HEPTANONE	I	I	I	I	I	I	I
HEXADECANOIC ACID	I	I	I	I	I	I	I
HEXALDEHYDE	A	X	A	X	X	A	A
HEXANE	X	X	C	C	X	A	A
HEXANOL	I	A	I	I	A	I	A
HEXENE	X	X	A	A	X	I	A
HEXYL METHYL KETONE	I	X	I	I	X	I	A
HEXYLAMINE	I	A	I	I	A	I	I
HEXYLENE GLYCOL	I	A	I	I	A	I	I
HEXYLALCOHOL	C	A	A	A	A	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
HISTOWAX	I	I	I	I	I	I	I
HYDRAULIC & MOTOR OIL	X	X	A	X	I	I	I
HYDRAZINE	X	X	A	X	I	I	I
HYDROBROMIC ACID	A	A	X	X	X	A	C
HYDROCHLORIC ACID	X	A	X	X	X	A	A
HYDROCHLORIC ACID	C	X	A	C	I	A	I
HYDROFLUORIC ACID	X	X	X	X	X	A	C
HYDROFLUOSILIC ACID	A	X	C	I	I	A	I
HYDROGEN CHLORIDE ANHYDROUS	I	I	I	I	I	I	I
HYDROGEN DIOXIDE (10%)	I	I	I	I	I	I	I
HYDROGEN GAS	A	A	A	A	A	A	A
HYDROGEN PEROXIDE OVER 10%	F	X	F	X	X	A	C
HYDROGEN PEROXIDE 10%	X	X	X	X	X	A	C
HYDROGEN SULFIDE (WET)	A	X	C	X	X	A	A
HYDROXY BENZENE	I	I	I	I	I	I	I
HYDROXYISOBUTYRONITRILE	I	I	I	I	I	I	I
HYDROXYTOLUENE	I	I	I	I	I	I	I
HYVAR XL	A	I	I	I	I	I	I
IMINODI-2-PROPANOL	I	I	I	I	I	I	I
IMINODIETHANOL	I	I	I	I	I	I	I
IODINE	C	C	X	C	C	A	C
IODINE PENTAFLUORIDE	X	X	X	X	X	C	I
IODOFORM	X	X	X	A	X	I	I
ISO-BUTANAL	I	I	I	I	I	I	I
ISO-BUTYLAMINE	I	I	I	I	I	I	I
ISO-BUTYLBROMIDE	I	I	I	I	I	I	I
ISO-BUTYLCARBINOL	I	I	I	I	I	I	I
ISO-OCTANE	I	I	I	I	I	I	I
ISOCYANATES	I	I	I	I	I	A	A
ISOOCTANE	X	X	C	A	X	A	A
ISOPROPYL ETHER	X	X	X	C	X	A	A
ISPOPROPYL ALCOHOL	A	A	C	C	A	A	A
ISPOROPYL ACETATE	X	X	X	X	X	A	A
JP-4 OIL	X	X	X	A	X	I	I
KEROSENE	X	X	C	A	X	A	A
KETONES	A	X	X	C	X	A	I
LACTIC ACID - COLD	X	A	A	X	A	A	C
LACTIC ACID - HOT	X	X	X	X	X	I	I
LAQUER SOLVENTS	X	X	X	X	X	A	A
LARD	X	X	C	A	X	A	A
LAVENDER OIL	X	X	X	A	X	A	A
LEAD ACETATE	A	A	A	A	X	A	A
LEAD NITRATE	A	A	A	A	A	I	I
LEAD SULFATE	A	I	A	I	I	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
LIME	A	I	C	X	I	I	I
LIME BLEACH	A	A	A	A	A	I	I
LIME SULFUR	A	X	A	X	X	A	A
LIMONENE	I	I	I	I	I	I	I
LINOLEIC ACID	X	X	X	A	X	I	I
LINSEED OIL	X	X	C	A	X	A	C
LIQUID PETROLEUM GAS (LPG)	X	X	A	A	X	I	A
LUBRICATING OILS	X	X	C	A	X	I	A
LYE SOLUTIONS	A	A	A	A	A	I	I
M E X	A	X	X	X	X	A	A
MAGNESIUM ACETATE	I	I	I	I	I	I	A
MAGNESIUM CHLORIDE	I	I	I	I	I	I	A
MAGNESIUM HYDRATE	I	A	I	I	A	A	A
MAGNESIUM HYDROXIDE	A	A	A	A	A	A	A
MAGNESIUM SULFATE & SULPHITE	A	A	A	A	A	A	A
MALEIC ACID	X	X	X	X	X	A	A
MALEIC ANHYDRIDE	X	X	X	X	X	I	I
MALIC ACID	X	C	C	C	C	A	C
MANGANOUS SULFATE	I	I	I	I	I	I	I
MAPP	A	I	A	A	A	I	I
MATHALLYL ALCOHOL	I	A	I	I	A	I	A
MERCURY	A	A	A	A	A	A	A
MERCURY VAPORS	A	A	A	A	A	A	A
MESITYL OXIDE	A	X	X	X	X	A	A
METHALLYL CHLORIDE	I	I	I	I	I	I	I
METHANE CARBOXYLIC ACID	X	I	A	I	I	I	I
METHANOIC ACID	I	I	I	I	I	I	I
METHANOL (METHYL ALCOHOL)	A	A	A	A	A	A	I
METHANOL (WOOD ALCOHOL)	A	A	A	A	A	A	A
METHOXY ETHANOL	I	I	I	I	I	I	I
METHOXYETHOXY ETHANOL	I	I	I	I	I	I	I
METHOXYPROPENYL BENZENE	I	I	I	I	I	I	I
METHYL 1-2,4-PENTANEDIOL	I	I	I	I	I	I	I
METHYL ACETOACETATE	A	X	X	X	X	I	A
METHYL ACETONE	I	F	I	I	X	A	A
METHYL ACETYLENE PROPADIENE	A	I	A	A	A	I	I
METHYL ALCOHOL	A	A	A	A	A	A	I
METHYL ALLYL ALCOHOL	I	I	I	I	I	I	I
METHYL ALLYL CHLORIDE	I	X	I	I	X	I	A
METHYL BROMIDE	X	X	X	C	X	A	A
METHYL BUTANE	I	I	I	I	I	I	I
METHYL BUTANE ALCOHOL	I	I	I	I	I	I	I
METHYL BUTYL KETONE	I	X	X	X	X	A	I
METHYL CARBITON	I	X	I	I	X	I	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
METHYL CELLOSOLVE	A	X	C	C	X	A	I
METHYL CHRLOIDE	X	X	X	X	X	I	A
METHYL CYANIDE	I	I	I	I	I	I	I
METHYL HEXANOL	I	A	I	I	A	A	A
METHYL METHACRYLATE	C	X	X	X	X	A	A
METHYL NORMAL AMYL KETONE	I	X	I	I	X	I	A
METHYL PROPYL ETHER	I	X	I	I	X	I	A
METHYL SALICYLATE	A	C	X	X	C	I	I
METHYL STYRENE	I	I	I	I	I	I	I
METHYL SULFIDE	I	I	I	I	I	I	I
METHYL TERTIARY BUTYL ETHER	I	I	X	X	X	A	I
METHYL-2-BUTANOL	I	X	I	I	A	I	A
METHYL-2-BUTANONE	I	X	I	I	X	I	A
METHYL-2-HEXANONE	I	X	I	I	X	I	A
METHYL-2-PENTANOL	I	I	I	I	I	I	I
METHYL-2-PENTANONE	I	I	I	I	I	I	I
METHYL-2-PROPEN-L-OL	I	I	I	I	I	I	I
"METHYL-3-PENTEN-1-ONE	"	I	I	I	I	I	I
METHYL-4-ISOPROPYL BENZENE	I	I	I	I	I	I	I
METHYL-ISO-AMYL-KETONE	I	I	I	I	I	I	I
METHYL-L-PROPANOL	I	I	I	I	I	I	I
METHYLALLYL ACETATE	I	X	I	I	X	I	A
METHYLAMYL ALCOHOL	I	A	I	I	A	I	A
METHYLAMYL CARBINOL	I	A	I	I	A	I	A
METHYLCYCLOHEXANE	I	X	I	I	X	I	A
METHYLENE BROMIDE	I	I	I	I	I	I	I
METHYLENE CHLORIDE	I	I	I	I	I	A	I
METHYLETHYL KETONE	A	X	X	X	X	A	A
METHYL HEXYL KETONE	X	I	I	I	I	I	A
METHYLISOBUTYL CARBINOL	A	A	A	A	A	I	C
METHYLISOBUTYL KETONE	I	X	I	I	X	I	A
METHYLISOBUTYL KETONE1	C	X	X	X	X	A	A
METHYLISOPROPYL KETONE	X	X	X	X	X	I	A
METHYLLACTONITRILE	I	I	I	I	I	I	I
METHYLPHENOL	I	I	I	I	I	I	I
METHYLPROPYL CARBINOL	I	I	I	I	I	I	I
METYL ACETATE	A	X	X	X	X	A	A
METYL BENZENE	I	X	I	I	X	I	A
MIL-A-6091	A	A	A	A	A	I	I
MIL-C-4339	X	X	X	A	X	I	I
MIL-C-7024	X	X	X	A	X	I	I
MIL-E-9500	A	A	A	A	A	I	I
MIL-F-16884	X	X	C	A	X	I	I
MIL-F-17111	X	X	A	A	X	I	I

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
MIL-F-25558 (RJ-1)	X	I	A	A	I	I	I
MIL-G-10924	X	X	X	A	X	I	I
MIL-G-25013	X	X	A	A	X	I	I
MIL-G-25537	X	I	A	A	I	I	I
MIL-G-3545	X	X	A	A	X	I	I
MIL-G-5572	X	X	X	A	X	I	I
MIL-G-7711	X	X	X	A	X	I	I
MIL-H-05606 (HFA)	X	I	A	A	I	I	I
MIL-H-13910	A	A	A	A	A	I	I
MIL-H-19457	A	X	X	X	X	I	I
MIL-H-22251	A	I	A	A	A	I	I
MIL-H-27601	X	I	A	A	I	I	I
MIL-H-5606 (J43)	X	I	A	X	I	I	I
MIL-H-6083	X	X	A	A	X	I	I
MIL-H-8446 (MLO-8515)	X	X	A	A	X	I	I
MIL-J-5161	X	X	X	A	X	I	I
MIL-J-5624 (JP-3, JP-4, JP-5)	X	X	X	A	X	I	I
MIL-L-15016	X	X	A	A	X	I	I
MIL-L-17331	X	X	A	A	X	I	I
MIL-L-2104	X	X	A	A	X	I	I
MIL-L-21260	X	X	A	A	X	I	I
MIL-L-23699	X	X	C	A	X	I	I
MIL-L-25681	A	I	A	A	I	I	I
MIL-L-3150	X	X	A	A	X	I	I
MIL-L-4343	C	X	A	A	X	I	I
MIL-L-6082	X	X	A	A	X	I	I
MIL-L-6085	X	X	X	A	X	I	I
MIL-L-7808	X	X	X	A	X	I	I
MIL-L-7870	X	X	A	A	X	I	I
MIL-L-9000	X	X	A	A	X	I	I
MIL-L-9236	X	X	X	A	X	I	I
MIL-P-27402	A	I	A	A	I	I	I
MIL-R-25576 (RP-1)	I	I	I	I	I	I	I
MIL-S-3136 TYPE 1 FUEL	X	X	A	A	X	I	I
MIL-S-3136 TYPE 2 FUEL	X	X	X	A	X	I	I
MIL-S-3136 TYPE 3 FUEL	X	X	X	A	X	I	I
MIL-S-3136 TYPE 4 OIL, LOWSWELL	X	X	A	A	X	I	I
MIL-S-3136 TYPE 5 OIL, MEDSWELL	X	X	A	A	X	I	I
MIL-S-3136 TYPE 6 OIL, HI SWELL	X	X	X	A	X	I	I
MIL-S-80187	A	I	A	A	I	I	I
MINERAL OIL	X	X	C	A	X	A	A
MINERAL SPIRITS	X	X	F	A	X	I	A
MOBILE HFA	X	I	I	X	I	I	I
MOLTEN SULFUR	I	X	I	I	X	X	X

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
MONO-CHLOROACETIC ACID	I	A	I	I	X	I	A
MONOBUTYL ETHER	I	X	I	I	X	I	A
MONOCHLOROBENZENE	X	X	X	X	X	X	A
MONOCHLORODIFLUOROMETHANE	I	X	I	I	X	I	C
MONOETHANOL AMINE	A	A	X	X	X	I	C
MONOETHYL AMINE	A	A	X	X	X	A	A
MONOETHYLAMINE	I	I	I	I	I	I	A
MORPHOLINE	X	I	I	X	I	I	I
MOTOR OIL, 40W	I	I	I	I	I	A	I
MTBE	I	I	X	X	X	A	I
MURIATIC ACID	F	A	X	X	X	A	A
N-BUTANAL	I	I	I	I	I	I	I
N-BUTYL BROMIDE	I	X	I	I	X	I	A
N-BUTYLAMINE	X	X	X	C	X	I	I
N-BUTYLBENZENE	I	X	I	I	X	I	A
N-BUTYLBUTYRATE	I	X	I	I	X	I	A
N-BUTYLCARBINOL	I	I	I	I	I	I	I
N-NONYL ALCOHOL	I	I	I	I	I	I	I
N-OCTANE	X	X	A	A	X	I	A
N-SERV (75% XYLENE)	I	I	I	I	I	I	C
NA-K	X	I	I	X	I	I	I
NAPTHA	X	X	X	C	X	A	A
NAPTHALENE	X	X	X	X	X	A	A
NAPTHENIC ACIDS	X	X	X	A	X	I	I
NATURAL GAS	X	X	X	X	X	I	X
NEOHEXANE	I	X	I	I	X	I	A
NEON GAS	A	A	A	A	A	I	I
NEU-TRI	I	X	I	I	X	I	A
NICKEL ACETATE	A	A	A	A	X	A	A
NICKEL CHLORIDE	A	A	A	A	A	A	A
NICKEL NITRATE	A	A	A	I	A	A	A
NICKEL SULFATE	A	A	A	A	A	A	A
NIETYLENE	I	A	I	I	I	I	I
NITRIC ACID, 10%	C	X	X	X	X	A	C
NITRIC ACID, 13N	I	I	I	I	I	I	I
NITRIC ACID 13N+5%	I	I	I	I	I	I	I
NITRIC ACID, 20%	A	X	X	X	X	A	A
NITRIC ACID, 30%	C	X	X	X	X	A	A
NITRIC ACID, 30-70%	F	X	X	X	X	A	A
NITRIC ACID, CONC (16N)	X	X	X	X	X	A	A
NITRIC ACID, RED FUMING	X	X	X	X	X	X	X
NITRILOTRIETHANOL	I	I	I	I	I	I	I
NITROBENZENE	X	X	X	X	X	A	A
NITROETHANE	A	A	C	X	A	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
NITROGEN	A	A	A	A	A	A	A
NITROMETHANE	A	A	C	X	C	A	A
NITROUS OXIDE GAS	I	I	I	I	I	I	I
NONANOIC ACID	I	I	I	I	I	I	I
NONANOL	I	I	I	I	I	I	I
NUTO H	X	I	I	A	I	I	I
NYVAC LIGHT	A	I	I	X	I	I	I
OCTANOIC ACID	I	I	I	I	I	I	I
OCTANOL	I	A	I	I	A	A	A
OCTYL ACETATE	I	X	I	I	X	A	A
OCTYL ALCOHOL	C	A	A	A	A	A	A
OCTYL ALDEHYDE	I	X	I	I	X	I	A
OCTYL AMINE	I	A	I	I	A	I	C
OCTYL CARBINOL	I	A	I	I	A	I	A
OCTYLENE GLYCOL	I	A	I	I	A	I	C
OIL-PETROLEUM	X	X	A	A	X	A	A
OLEIC ACID	X	X	X	C	X	A	A
OLEUM (FUMING SULFURIC ACID)	X	X	X	C	X	X	X
OLIVE OIL	A	X	A	A	X	A	C
ORTHO-DICHLOROBENZENE	X	X	X	X	X	I	A
ORTHO-DICHLOROBENZOL	I	X	I	I	X	I	A
ORTHOXYLENE	I	X	I	I	X	I	A
OXALIC ACID	A	X	X	X	X	A	C
OXYDIETHANOL	I	I	I	I	I	I	I
OZONE	A	X	C	X	X	C	C
P-CYMENE	X	X	X	X	X	A	A
PAINT THINNER	X	X	X	X	X	A	I
PALMITIC ACID	C	X	C	A	X	C	A
PAPERMAKERS ALUM	A	A	A	A	A	A	A
PARA-DICHLOROBENZENE	X	X	X	X	X	I	A
PARAFFIN WAX	X	X	A	A	X	A	X
PARALDEHYDE	I	F	I	I	I	I	A
PARAXYLENE	I	X	I	I	X	I	A
PCB	I	I	I	I	I	I	I
PEHENYLMETHANOL	I	I	I	I	I	I	I
PELARGONIC ALCOHOL	I	X	I	I	X	I	A
PENTACHLOROETHANE	I	X	I	I	X	I	A
PENTADIONE	I	I	I	I	I	I	I
PENTAMETHYLENE	I	I	I	I	I	I	I
PENTANE	X	X	A	A	X	A	A
PENTANOL	I	I	I	I	I	I	I
PENTANONE	I	X	I	I	X	I	A
PENTASOL	I	A	A	I	A	I	A
PENTYL ACETATE	I	I	I	I	I	I	I

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
PENTYL ALCOHOL	I	I	I	I	I	I	I
PENTYL BROMIDE	I	I	I	I	I	I	I
PENTYL CHLORIDE	I	I	I	I	I	I	I
PENTYL ETHER	I	I	I	I	I	I	I
PENTYLAMINE	I	I	I	I	I	I	I
PERCHLORIC ACID-2N	C	X	C	X	X	A	I
PERCHLOROETHYLENE	X	X	X	X	X	A	A
PERCHLOROMETHANE	I	I	I	I	I	I	I
PETROLEUM CRUDE	X	X	A	A	X	A	A
PETROLEUM ETHER	X	X	I	A	X	I	A
PETROLEUM OILS	X	X	A	X	X	A	A
PHENBO	I	I	I	I	I	A	I
PHENOL	X	X	X	X	X	A	A
PHENOSULFONIC ACID	I	X	I	I	X	A	A
PHENYLAMINE	I	I	I	I	I	I	I
PHENYLBROMIDE	I	I	I	I	I	I	I
PHENYLBUTANE	I	I	I	I	I	I	I
PHENYLCHLORIDE	I	X	I	I	X	I	A
PHENYLETHYLENE	I	I	I	I	I	I	I
PHENYLMETHANE	I	I	I	I	I	I	I
PHENYLMETHYL ACETATE	I	I	I	I	I	I	I
PHOSPHATE ESTERS	A	I	I	X	I	I	I
PHOSPHORIC ACID 10%	X	A	X	X	A	A	A
PHOSPHORIC ACID 10%-85%	X	A	X	X	X	A	A
PHOSPHORUS TRICHLORIDE	A	X	X	X	X	I	I
PICRIC ACID, H2O SOLUTION	X	A	C	X	A	I	I
PINE OIL	X	X	X	X	X	A	
PINENE	X	X	F	A	X	A	A
POLYCHLORINATED BIPHENOL	I	I	I	I	I	I	I
POLYETHYLENE GLYCOL E-400	I	A	I	I	A	I	I
POLYOL ESTER	X	X	X	A	I	I	I
POLYPROPYLENE GLYCOL	I	A	I	I	A	I	I
POTASSIUM ACETATE	A	X	A	A	X	A	A
POTASSIUM BISULFATE	I	A	I	I	I	A	A
POTASSIUM BISULFITE	I	A	I	I	I	A	I
POTASSIUM CARBONATE	A	A	A	I	A	A	A
POTASSIUM CHLORIDE	A	A	A	A	A	A	A
POTASSIUM CHROMATE	I	I	I	I	I	A	A
POTASSIUM CYANIDE	A	A	A	A	A	A	A
POTASSIUM DICHROMATE	A	A	A	A	A	A	A
POTASSIUM HYDRATE	I	A	I	I	A	I	A
POTASSIUM HYDROXIDE	A	A	C	X	A	A	A
POTASSIUM NITRATE	A	A	A	A	A	A	A
POTASSIUM PERMANGANATE, 5%	I	I	I	I	I	A	I

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
POTASSIUM SILICATE	I	A	I	I	A	I	A
POTASSIUM SULFATE	A	A	A	A	A	A	A
POTASSIUM SULFIDE	I	I	I	I	I	A	I
POTASSIUM SULFITE	A	A	A	I	A	I	A
PRESTONE ANTIFREEZE	A	I	A	A	I	I	I
PRODUCER GAS	X	X	A	A	A	I	I
PROPANE	X	X	C	A	X	I	A
PROPANEDIOL	I	A	I	I	A	I	I
PROPANETRIOL	I	I	I	I	I	I	I
PROPANOL	I	A	I	I	A	I	A
PROPANOLAMINE	I	I	I	I	I	I	I
PROPANONE	I	I	I	I	I	I	I
PROPEN-L-OL	I	I	I	I	I	I	I
PROPENEDIAMENE	I	I	I	I	I	I	I
PROPENENITRILE	I	I	I	I	I	I	I
PROPENYALISOLE	I	I	I	I	I	I	I
PROPENYL ALCOHOL	I	I	I	I	I	I	I
PROPIONIC ACID	A	I	I	X	I	I	A
PROPIONITRILE	X	I	A	A	I	I	I
PROPYL ACETATE	A	X	X	X	X	A	A
PROPYL ALCOHOL	A	A	A	A	A	A	A
PROPYL ALDEHYDE	I	F	I	I	I	A	A
PROPYL BENZENE	I	I	I	I	I	I	I
PROPYL CHLORIDE	I	X	I	I	X	A	A
PROPYL DIAMINE	I	A	I	I	A	I	I
PROPYL ETHER	I	I	I	I	I	I	I
PROPYL NITRATE	I	X	X	X	X	I	I
PYDRAUL 'E' SERIES	A	X	X	X	X	A	A
PYDRAULIC 'C'	X	I	X	X	I	I	I
RED OIL	X	X	A	A	X	I	I
REFRIGERANT 11	X	I	X	A	I	I	I
REFRIGERANT 12	X	I	A	A	I	I	I
REFRIGERANT 22	X	I	A	X	I	I	I
RESORCINOL	I	I	I	X	I	I	I
SAE NO. 10 OIL	I	I	C	A	I	I	I
SAL AMMONIAC	A	A	A	A	A	I	I
SEA WATER	A	A	A	A	A	A	A
SEWAGE	F	F	A	A	F	A	A
SILICATE ESTERS	X	X	A	A	X	I	I
SILICATE OF SODA	I	A	I	I	A	I	A
SILICONE GREASE	A	A	A	A	A	I	I
SILICONE OIL	A	A	A	A	A	A	I
SILVER NITRATE	A	A	A	A	A	A	A
SKYDROL 500 TYPE 2	A	I	X	X	I	I	I

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
SKYDROL 500B	A	I	X	I	I	I	I
SKYDROL 500C	I	I	X	I	I	I	I
SKYDROL 70000 TYPE 2	A	I	X	X	I	I	I
SOAP SOLUTIONS	A	A	A	A	A	I	A
SODA ASH	A	A	A	A	A	A	A
SODA LIME	I	A	I	I	A	A	A
SODA NITER	I	A	I	I	A	I	A
SODA, CAUSTIC	I	A	I	I	A	A	A
SODIUM ACETATE	A	X	A	A	X	A	A
SODIUM ALUMINATE	I	A	I	I	A	A	A
SODIUM BICARBONATE	A	A	A	A	A	A	A
SODIUM BISULFITE	A	A	A	A	A	A	C
SODIUM BORATE	A	A	A	A	A	A	A
SODIUM CARBONATE 10%-15%	A	A	A	A	A	A	A
SODIUM CHLORIDE	A	A	A	A	A	A	A
SODIUM CYANIDE	A	A	A	A	A	A	A
SODIUM DICHROMATE	A	C	C	C	C	A	A
SODIUM HYDRATE	I	A	I	I	A	I	A
SODIUM HYDROCHLORITE	A	X	X	X	X	I	A
SODIUM HYDROXIDE (CAUSTIC SODA)	A	A	A	X	A	A	A
SODIUM HYPOCHLORITE	A	X	X	A	X	A	A
SODIUM METAPHOSPHATE	A	A	A	A	A	A	A
SODIUM NITRATE	A	A	A	A	A	A	A
SODIUM PERBORATE	A	A	A	A	A	A	A
SODIUM PEROXIDE	A	A	A	A	A	A	A
SODIUM PHOSPHATE	A	A	A	A	A	A	A
SODIUM SILICATE	A	A	A	A	A	A	A
SODIUM SULFATE	A	A	A	A	A	A	A
SODIUM SULFIDE	A	A	A	A	A	I	A
SODIUM SULFITE	A	A	A	A	A	A	A
SODIUM THIOSULFATE	A	A	A	A	A	A	A
SOYBEAN OIL	C	X	A	A	X	A	A
STANNIC SULFIDE	I	A	I	I	A	I	A
STANNOUS CHLORIDE	A	A	A	A	A	A	A
STANNOUS SULFIDE	I	A	I	I	A	I	A
STEAM, BELOW 350F	A	X	X	X	X	X	X
STEARIC ACID	A	X	A	A	X	A	I
STODDARD SOLVENT	X	X	A	A	X	A	A
STYRENE	X	X	X	X	X	A	A
SULFAMIC ACID	A	A	A	A	A	I	C
SULFUR	F	X	X	X	X	A	X
SULFUR CHLORIDE	X	X	C	C	X	A	A
SULFUR DIOXIDE	A	C	X	X	C	A	C
SULFUR TRIOXIDE, DRY	A	A	X	X	A	X	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
SULFURIC ACID 60% (200F)	I	I	I	I	I	X	X
SULFURIC ACID, CONC TO 98%	X	X	X	X	X	A	A
SULFURIC ACID, FUMING	X	X	X	X	X	X	X
SULFURIC ACID, 25%	A	A	X	X	X	A	A
SULFURIC ACID, 25%-50%	A	A	X	X	X	A	A
SULFURIC ACID, 50%-96%	X	X	X	X	X	A	A
SULFUROUS ACID, 10%	A	A	X	X	A	A	A
SULFUROUS ACID 10%-85%	A	A	X	X	X	A	A
T-BUTYL AMINE	A	I	I	I	I	I	I
TALL OIL	X	X	A	A	X	A	C
TALLOW	X	X	A	A	X	A	C
TANNIC ACID	A	A	A	A	F	A	C
TAR	X	X	A	X	X	X	X
TAR BITUMINOUS	X	X	C	A	X	I	I
TARTARIC ACID	A	C	A	A	X	A	C
TELONE 2	I	I	I	I	I	I	A
TERPINOL	C	X	X	A	X	A	A
TERTIARY BUTYL ALCOHOL	A	A	A	A	A	I	A
TERTIARY BUTYL ALMINE	A	I	I	I	I	I	I
TERTIARY BUTYL MERCAPTAN	X	X	X	X	X	I	I
TETRACHLOROBENZENE	I	X	I	I	X	I	A
TETRACHLOROETHYLENE	X	X	X	X	X	A	A
TETRACHLOROMETHANE	I	X	I	I	X	I	A
TETRACHLORONAPTHALENE	I	X	I	I	X	I	A
TETRAETHYLENE GLYCOL	I	A	I	I	A	I	I
TETRAHYDROFURAN	X	X	X	I	X	I	C
TETRETHYLOROSILICATE	I	I	I	X	I	I	I
THF	I	I	I	I	I	I	C
TIN CHLORIDE	I	A	I	A	A	A	A
TITANIUM TETRACHLORIDE	X	X	X	X	X	A	I
TOLUENE	X	X	X	I	X	A	I
TOLUIDINE	I	I	I	I	I	I	I
TOLUOL	I	I	I	I	I	I	I
TRANSFORMER OIL	X	X	A	A	X	A	I
TRANSMISSION 'A' OIL	X	X	A	A	X	I	F
TRI (2-HYDROXYETHYL) AMINE	I	I	I	I	I	I	I
TRIBUTYL PHOSPHATE	I	X	X	X	X	A	A
TRIBUTYLAMINE	I	A	A	I	A	I	I
TRICHLOROBENZENE	I	X	I	I	X	I	A
TRICHLOROETHANE	X	X	X	X	X	I	A
TRICHLOROETHYLENE	X	X	X	X	X	A	A
TRICHLOROMETHANE	I	I	I	I	I	I	I
TRICHLOROTOLUENE	I	I	I	I	I	I	I
TRICHOLOROACETIC ACID	A	C	X	A	A	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
TRICRESYL PHOSPHATE	X	X	X	X	X	I	X
TRIETHANOLAMINE	A	A	A	C	X	A	A
TRIETHYLAMINE	I	A	I	I	A	I	I
TRIETHYLENE GLYCOL	I	A	I	I	A	I	I
TRIHYDROXYBENZOIC ACID	I	I	I	I	I	I	I
TRIMETHYL PENTANES (MIXED)	I	I	I	I	I	I	I
TRIMETHYL PENTENE	I	I	I	I	I	I	I
TRIMETHYLAMINE	I	I	I	I	I	A	A
TRISODIUM PHOSPHATE	A	A	A	A	A	I	A
TRITOYL PHOSPHATE	I	I	I	I	I	I	I
TUNG OIL	I	I	A	I	I	A	I
TUNG OIL (CHINA OIL)	X	X	A	A	X	A	A
TURPETINEX	X	X	X	X	X	A	A
UDMH	A	A	A	A	A	I	I
UNDECYL ALCOHOL	I	I	I	I	I	I	I
UREA	I	I	A	I	A	A	A
URETHANE FORMULATIONS	I	I	I	A	I	I	I
URIC ACID	I	I	I	I	I	I	I
VARNISH	X	X	X	A	X	I	I
VEGETABLE OILS	C	X	C	A	X	A	A
VERSILUBE F44	I	I	I	A	I	I	I
VERSILUBE F55	X	I	I	A	I	I	I
VINEGAR	A	A	F	X	F	X	X
VINEGAR ACID	I	I	I	I	I	I	I
VINYL ACETATE	I	X	I	I	X	A	A
VINYL BENZENE	I	X	I	I	X	A	A
VINYL CHLORIDE	X	X	X	X	X	A	A
VINYL CYANIDE	I	I	I	I	I	I	I
VINYL ETHER	I	X	I	I	X	A	A
VINYL STRYENE	I	I	I	I	I	I	I
VINYL TOLUENE	I	X	I	I	X	A	A
VINYL TRICHLORIDE	I	X	I	I	X	A	A
VITAL, 4300	I	X	I	I	X	I	I
VM&P NAPTHA	X	X	F	A	X	I	X
WATER	A	A	A	A	F	A	A
WATER, BOILING	A	I	A	I	I	X	X
WATER, SODA	I	I	I	I	I	I	I
WEMCO C	X	X	A	A	X	I	I
WHISKEY	A	A	A	A	A	X	X
WHITE OIL	X	X	A	A	X	A	A
WHITE PINE OIL	X	X	X	A	X	I	I
WINES	A	A	A	A	A	X	X
WOOD ALCOHOL	A	A	A	A	A	A	A
WOOD OIL	X	X	A	A	X	A	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data

CHEMICAL RESISTANCE CHART

MATERIAL	EPDM	GUM	NEO	NITRILE	SBR	UHMW	XLPE
XENON	A	A	A	A	A	I	I
XYLENE, XYLOL	X	X	X	X	X	A	A
XYLIOINE	A	C	C	C	C	A	A
ZEOLITES	A	A	A	A	A	I	I
ZINC ACETATE	A	A	A	A	X	I	I
ZINC CARBONATE	I	A	I	I	A	A	A
ZINC CHLORIDE	A	A	A	A	A	A	A
ZINC CHROMATE	I	I	I	I	I	I	A
ZINC SULFATE	A	A	A	A	A	I	A

Rating Guide

A – Acceptable Performance
C – Conditional Performance
F – Fair Performance
X – Not Recommended
I – Insufficient Data