4444 Homestead Road ▪ Houston, Texas 77028
800.231.7116 **(Toll-Free)** 800.759.4673 **(Fax)**
texcelrubber.com

TEX-NEO40

40 Duro Neoprene Sheet

General Properties and Applications

A softer durometer neoprene used for gaskets and sealing where surface irregularities or configuration requires a more pliable material. Provides medium oil and ozone resistance. Our exclusive post-cure process provides a smooth and clean finish that is free of talc, a must for PSA applications.

TECHNICAL DATA

Durometer	40 +/-5
Color	Black
Temperature	-20°F to +190°F
Tensile Strength	1,000 psi
Elongation	350%
Specifications	ASTM D2000-M1-BC407

Width	Gauge	Part Number	Ln. Ft./Roll	Sq. Yds./Roll	Lbs./Roll
48"	1/16"	NEO40-2-48	50'	22.2	94
	1/8"	NEO40-4-48	50'	22.2	188
	3/16"	NEO40-6-48	50'	22.2	282
	1/4"	NEO40-8-48	50'	22.2	377
	3/8"	NEO40-12-48	30'	13.3	300
	1/2"	NEO40-16-48	30'	13.3	407
	3/4"	NEO40-24-48	30'	13.3	610
	1"	NEO40-32-48	30'	13.3	814