



TECHNICAL DATA	
Durometer	73 +/-5
Color	Red
Temperature	-20°F to +180°F
Tensile Strength	700 psi
Elongation	250%
	·

General Properties and Applications

The industry's general service rubber for common gasketing applications, such as water. Our exclusive post-cure process provides a smooth and clean finish that is free of talc, a must for PSA applications

Note:

- Not recommended for applications with oil.
- Talc-free surface eliminates the need to clean the sheet rubber and is ideal for PSA applications.
- Certificates of Conformance indicating production date and lot code are available on request at the time of order.





Width	Gauge	Part Number	Ln. Ft./Roll	Lbs./Roll
36"	1/16"	RED-2-36	60'	100
	1/8"	RED-4-36	30'	100
	3/16"	RED-6-36	40'	200
	1/4"	RED-8-36	30'	200
	3/8"	RED-12-36	20'	200
48"	1/16"	RED-2-48	45'	200
		RED-2-48-100	100'	220
	1/8"	RED-4-48	23'	100
		RED-4-48-50	50'	217
	3/16"	RED-6-48	30'	200
	1/4"	RED-8-48	23'	200